



EPIMAX HIGH FLOW, HIGH IMPACT ABS-808F TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	7 ft-lbs/in
Tensile Strength	D-638	8,700 psi
Tensile Modulus	D-638	375,000 psi
Flexural Strength	D-790	14,200 psi
Flexural Modulus	D-790	385,000 psi
Rockwell Hardness	D-785	95 R
Specific Gravity	D-792	1.05
HDTUL Unannealed (264 psi)	D-648	190 °F
Mold Shrinkage	D-955	0.004 – 0.006 in/in
Melt Flow Index	D-1238 (220°C/10kg)	15 g/10 min
Flammability	UL-94 ²	HB (1.5 mm)

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²EPI laboratory test values pending UL recognition.

ABS

ABS-808F

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company