



## EPITEC 30% GLASS FIBER REINFORCED ABS-853G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE <sup>1</sup>
Izod Impact	D-256	1.2 ft-lbs/in
Tensile Strength	D-638	13,500 psi
Tensile Modulus	D-638	1,150,000 psi
Flexural Strength	D-790	17,500 psi
Flexural Modulus	D-790	1,100,000 psi
Rockwell Hardness	D-785	110 R
Specific Gravity	D-792	1.27
HDTUL Unannealed (264 psi)	D-648	220 °F
Mold Shrinkage	D-955	0.002-0.003 in/in
Flammability	UL-94 <sup>2</sup>	HB (1.5 mm)

<sup>1</sup>Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

<sup>2</sup>EPI laboratory test values pending UL recognition.

# ABS

## ABS-853G

EPI • 2255 Westover Road, Chicopee, MA 01022  
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company