



EPI TEC HIGH FLOW PC/ABS-310F TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	10.0 ft-lbs/in
Tensile Strength	D-638	7,500 psi
Tensile Modulus	D-638	350,000 psi
Elongation at Break	D-638	135 %
Flexural Strength	D-790	12,100 psi
Flexural Modulus	D-790	330,000 psi
Rockwell Hardness	D-785	115 R
Specific Gravity	D-792	1.15
HDTUL Unannealed (264 psi)	D-648	230 °F
Mold Shrinkage	D-955	0.005-0.007 in/in
Melt Flow Index	D-1238 (230°C/3.8kg)	5.2 g/10 min
Flammability	UL-94 ²	HB (1.5 mm)

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²EPI laboratory test values pending UL recognition.

PC/ABS

PC/ABS-310F

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company