



EPITEC 20% GLASS FIBER REINFORCED PC/ABS-352G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	1.6 ft-lbs/in
Tensile Strength	D-638	13,400 psi
Tensile Modulus	D-638	920,000 psi
Flexural Strength	D-790	19,100 psi
Flexural Modulus	D-790	855,000 psi
Rockwell Hardness	D-785	112 R
Specific Gravity	D-792	1.30
HDTUL Unannealed (264 psi)	D-648	255 °F
Mold Shrinkage	D-955	0.0025 in/in

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

PC/ABS

PC/ABS-352G

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



ENGINEERED POLYMERS
INDUSTRIES



Osterman

A Division of Osterman & Company