



## EPIMAX EXTRUSION GRADE PC-900E TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE <sup>1</sup>
Izod Impact	D-256	16 ft-lbs/in
Tensile Strength	D-638	8,900 psi
Tensile Modulus	D-638	315,000 psi
Flexural Strength	D-790	13,500 psi
Flexural Modulus	D-790	345,000 psi
Rockwell Hardness	D-785	113 R
Specific Gravity	D-792	1.20
HDTUL Unannealed (264 psi)	D-648	270 °F
Mold Shrinkage	D-955	0.005-0.007 in/in
Melt Flow Index	D-1238 (300°C/1.2kg)	4 g/10 min

<sup>1</sup>Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

# PC

## PC-900E

EPI • 2255 Westover Road, Chicopee, MA 01022  
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company