



EPI MAX IGNITION RESISTANT PC-920FR TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	13 ft-lbs/in
Tensile Strength	D-638	8,900 psi
Tensile Modulus	D-638	345,000 psi
Flexural Strength	D-790	14,200 psi
Flexural Modulus	D-790	340,000 psi
Rockwell Hardness	D-785	123 R
Specific Gravity	D-792	1.2
HDTUL Unannealed (264 psi)	D-648	260 °F
Mold Shrinkage	D-955	0.005-0.007 in/in
Melt Flow Index	D-1238 (300°C/1.2kg)	20 g/10 min
Flammability	UL-94 ²	V-0 (1.5 mm) 5VA (3.0 mm)
RTI	UL-746B ²	
Elec		125 °C
Mech Imp		105 °C
Mech Str		125 °C
Weatherability	UL-746 ^{2,3}	f1

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²UL recognized (File #E123498)

³Suitable for outdoor use with respect to exposure to ultraviolet light, water exposure and immersion in accordance with UL-746C.

PC

PC-920FR

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company