



## EPIMAX HIGH HEAT, UV RESISTANT PC-944HV TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE <sup>1</sup>
Izod Impact	D-256	17 ft-lbs/in
Tensile Strength	D-638	10,500 psi
Tensile Modulus	D-638	350,000 psi
Flexural Strength	D-790	14,000 psi
Flexural Modulus	D-790	350,000 psi
Rockwell Hardness	D-785	118 R
Specific Gravity	D-792	1.2
HDTUL Unannealed (264 psi)	D-648	265 °F
Mold Shrinkage	D-955	0.005-0.007 in/in
Melt Flow Index	D-1238 (300°C/1.2kg)	10 g/10 min
Flammability	UL-94 <sup>2</sup>	V-2 (1.5 mm) V-2 (3.0 mm)
RTI (3.0 mm)	UL-746B <sup>2</sup>	Elec 120 °C
Mech Imp		110 °C
Mech Str		120 °C
Weatherability	UL-746 <sup>2,3</sup>	f1

<sup>1</sup>Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

<sup>2</sup>UL recognized (File #E123498)

<sup>3</sup>Suitable for outdoor use with respect to exposure to ultraviolet light, water exposure and immersion in accordance with UL-746C.

# PC

## PC-944HV

EPI • 2255 Westover Road, Chicopee, MA 01022  
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company