



EPI MAX 40% GLASS FIBER REINFORCED PC-954G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	1.8 ft-lbs/in
Tensile Strength	D-638	22,700 psi
Tensile Modulus	D-638	1,600,000 psi
Flexural Strength	D-790	27,800 psi
Flexural Modulus	D-790	1,350,000 psi
Rockwell Hardness	D-785	91 M
Specific Gravity	D-792	1.52
HDTUL Unannealed (264 psi)	D-648	295 °F
Mold Shrinkage	D-955	0.001-0.002 in/in
Flammability	UL-94 ²	V-0 (1.5 mm) 5VA (3.0 mm)

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²EPI laboratory test values pending UL recognition.

PC

PC-954G

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company