



## EPITEC 15% GLASS FIBER REINFORCED PC-951G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE <sup>1</sup>
Izod Impact, 73 °F	D-256	2.0 ft-lbs/in
Tensile Strength	D-638	11,000 psi
Tensile Modulus	D-638	625,000 psi
Flexural Strength	D-790	17,900 psi
Flexural Modulus	D-790	690,000 psi
Rockwell Hardness	D-785	121 R
Specific Gravity	D-792	1.30
HDTUL Unannealed (264 psi)	D-648	285 °F
Mold Shrinkage	D-955	0.002-0.004 in/in
Flammability	UL-94 <sup>2</sup>	V-0 (1.5 mm) 5VA (3.0 m)

<sup>1</sup>Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

<sup>2</sup>EPI laboratory values pending UL recognition.

# PC

## PC-951G

EPI • 2255 Westover Road, Chicopee, MA 01022  
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company