



EPITEC 20% GLASS FIBER REINFORCED PC-952G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact, 73 °F	D-256	2.0 ft-lbs/in
Tensile Strength	D-638	15,800 psi
Tensile Modulus	D-638	850,000 psi
Flexural Strength	D-790	19,500 psi
Flexural Modulus	D-790	810,000 psi
Rockwell Hardness	D-785	93 M
Specific Gravity	D-792	1.35
HDTUL Unannealed (264 psi)	D-648	295 °F
Mold Shrinkage	D-955	0.002-0.003 in/in
Flammability	UL-94 ²	V-0 (1.5 mm) 5VA (3.0 m)

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²UL recognized (File #123498)

PC

PC-952G

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



ENGINEERED POLYMERS
INDUSTRIES



A Division of Osterman & Company