



EPITEC 5% GLASS FIBER REINFORCED PC-955G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact, 73 °F	D-256	2.5 ft-lbs/in
Tensile Strength	D-638	9,200 psi
Tensile Modulus	D-638	395,000 psi
Flexural Strength	D-790	14,200 psi
Flexural Modulus	D-790	530,000 psi
Rockwell Hardness	D-785	120 R
Specific Gravity	D-792	1.23
HDTUL Unannealed (264 psi)	D-648	275 °F
Mold Shrinkage	D-955	0.002-0.004 in/in
Flammability	UL-94 ²	V-0 (1.5 mm) 5VA (3.0 m)

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

²EPI laboratory values pending UL recognition.

PC

PC-951G

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company