



EPIVAL GLASS FIBER REINFORCED PC-900G TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	VALUE ¹
Izod Impact	D-256	2.3 ft-lbs/in
Tensile Strength	D-638	9,400 psi
Tensile Modulus	D-638	405,000 psi
Flexural Strength	D-790	15,600 psi
Flexural Modulus	D-790	550,000 psi
Rockwell Hardness	D-785	121 R
Specific Gravity	D-792	1.25
HDTUL Unannealed (264 psi)	D-648	275 °F
Mold Shrinkage	D-955	0.002-0.004 in/in

¹Typical values are an average of NATURAL color samples tested and based on common ASTM procedures. This data is presented as a guide and does not reflect product specifications for particular properties.

All Epival materials use recycled materials from post-consumer and/or post-industrial feedstreams.

PC

PC-900G

EPI • 2255 Westover Road, Chicopee, MA 01022
Tel 413-593-9600 • Fax 413-593-9609



A Division of Osterman & Company